



Restorative Aspects of Adhesive Dentistry

Mohamed Moustafa Awad*

College of Dentistry, Prince Sattam Bin Abdulaziz University, Alkharj, Saudi Arabia

***Corresponding Author:** Mohamed Moustafa Awad, College of Dentistry, Prince Sattam Bin Abdulaziz University, Alkharj, Saudi Arabia.**Received:** November 06, 2017; **Published:** November 13, 2017

Adhesion is the driving force of the progress in dentistry [1]. Many clinical applications in restorative dentistry are indeed adhesive procedures including the placement or repair of direct and indirect restorations.

In the direct restorative procedures, the main challenge is to achieve robust bonding to tooth structure. Based on the dental substrate, adhesive strategy is selected. Current adhesive strategies include; etch-and-rinse (ER), self-etching (SE) and selective enamel etching (SEE). ER strategy in which phosphoric acid etchant is applied to dental substrate prior to adhesive application is recommended for enamel, while it may be considered an aggressive step to dentin [2]. Acid-etching of dentin activates the matrix metalloproteinases enzymes which may result in degradation of collagen fibrils within hybrid layer which can affect bond strength [3,4]. In contrast to ER, SE strategy do not require the acid-etching step, as they contain acidic monomers that simultaneously 'condition' and 'prime' the dental substrate [5]. This strategy is more recommended for resin-dentin bonding more than enamel. In SEE, acid-etching is performed only to enamel followed by application of SE or multi-mode (MM) -universal- adhesive to both enamel and dentin [6]. MM adhesives are primarily SE adhesives that can be used in ER, SE or SEE approaches [7].

Clinician should consider clinical approaches to enhance the durability of adhesive bonding to tooth substrates such as vigorous rubbing application, prolonging the exposure time during light curing, application of multiple coats and effective solvent evaporation [8].

In contrast to direct resin-based restoratives which usually are applied in the preset form, and covalently bond to cured adhesives, the indirect restorations are mostly made of ceramics or indirect composite which is highly polymerized. The main challenge is the achievement of reliable bonding between the resin cement and indirect material. Two-step surface treatment is suggested based on the composition of indirect material [9]. Firstly, micromechanical surface treatment using hydrofluoric acid etching for glass-based [10] or hybrid ceramics [11], air-abrasion for polycrystalline ceramic [12] or indirect composite [13].

Following micromechanical surface treatment, the adhesion promoter or so-called [primers] can be applied to enhance chemical bonding between the indirect material and resin cement. Primers include γ -methacryloxypropyltrimethoxysilane (silane) which can be used for glass-based [14], hybrid ceramics [11] and indirect composites [13] or 10-methacryloyloxydecyl dihydrogen phosphate (MDP)-Containing primer for polycrystalline ceramics [15]. The recently introduced universal adhesives improved bond strength to zirconia ceramic [16]. However, regardless of its silane content universal adhesives cannot be considered as alternatives to the silane-based primers for glass-based ceramics [17].

The success of both direct and indirect restorations can be affected by the bonding quality achieved. Therefore, clinician should be aware of the nature of substrates to be bonded as well as the recommended adhesive strategy or surface treatment.

Bibliography

1. Roulet JF. "Editorial: a day in the life of a restorative dentist". *The Journal of Adhesive Dentistry* 13.4 (2011): 303.
2. Pashley DH., et al. "State of the art etch-and-rinse adhesives". *Dental Materials* 27.1 (2011): 1-16.
3. Carrilho MR., et al. "In vivo preservation of the hybrid layer by chlorhexidine". *Journal of Dental Research* 86.6 (2007): 529-533.
4. Zhang SC and Kern M. "The role of host-derived dentinal matrix metalloproteinases in reducing dentin bonding of resin adhesives". *International Journal of Oral Science* 1.4 (2009): 163-176.
5. Van Meerbeek B., et al. "State of the art of self-etch adhesives". *Dental Materials* 27.1 (2011): 17-28.
6. Hanabusa M., et al. "Bonding effectiveness of a new 'multi-mode adhesive to enamel and dentine". *Journal of Dentistry* 40.6 (2012): 475-484.
7. Wagner A., et al. "Bonding performance of universal adhesives in different etching modes". *Journal of Dentistry* 42.7 (2014): 800-807.
8. Reis A., et al. "Overview of clinical alternatives to minimize the degradation of the resin-dentin bonds". *Operative Dentistry* 38.4 (2013): E1-E25.
9. Awad MM., et al. "Adhesive Bonding to Computer-aided Design/ Computer-aided Manufacturing Esthetic Dental Materials: An Overview". *The Journal of Contemporary Dental Practice* 18.7 (2017): 622-626.
10. Hooshmand T., et al. "Bond durability of the resin-bonded and silane treated ceramic surface". *Dental Materials* 18.2 (2002): 179-188.
11. Campos F., et al. "Resin Bonding to a Hybrid Ceramic: Effects of Surface Treatments and Aging". *Operative Dentistry* 41.2 (2016): 171-178.
12. Chen L., et al. "Evaluation of silica-coating techniques for zirconia bonding". *American Journal of Dentistry* 24.2 (2011): 79-84.
13. Spitznagel FA., et al. "Resin bond to indirect composite and new ceramic/polymer materials: a review of the literature". *Journal of Esthetic and restorative Dentistry* 26.6 (2014): 382-393.
14. Lung CY and Matinlinna JP. "Aspects of silane coupling agents and surface conditioning in dentistry: an overview". *Dental Materials* 28.5 (2012): 467-477.
15. Kern M. "Bonding to oxide ceramics-laboratory testing versus clinical outcome". *Dental Materials* 31.1 (2015): 8-14.
16. Amaral M., et al. "The potential of novel primers and universal adhesives to bond to zirconia". *Journal of Dentistry* 42.1 (2014): 90-98.
17. Yoshihara K., et al. "Effectiveness and stability of silane coupling agent incorporated in 'universal' adhesives". *Dental Materials* 32.10 (2016): 1218-1225.

Volume 1 Issue 7 December 2017**© All rights are reserved by Mohamed Moustafa Awad.**